

# Enameled wires

## Thermex<sup>®</sup> 240 FL

- Enameled winding wire with outstanding thermal and chemical properties
- Insulation based on aromatic polyimide enamel
- Temperature Index 240

### General description

THERMEX<sup>®</sup> 240 rectangular-shaped wires are insulated with an aromatic polyimide varnish. The insulation provides outstanding thermal and chemical properties and a high flexibility.

### Application

- Motor windings with operating temperatures up to 220 °C
- Motors and generators for the aviation and marine industries.
- Motors and equipment in the nuclear and cryogenic field.

### Conventional Types

Rectangular copper wires:

- Thickness: 1.00 to 5.00 mm
- Width: 2.00 to 12 mm
- Cross-section: 2 to 60 mm<sup>2</sup>
- Coating class: Grade 1 and Grade 2

### Standards

THERMEX<sup>®</sup> 240 flat wires meet the requirements of IEC 60317-47. The standard dimensions of the conductors (nominal dimension) and the tolerances comply with the standard IEC 60317-0-2.

The test methods are based on IEC Publication 60851:

- 60851-1 General
- 60851-2 Definition of dimensions
- 60851-3 Mechanical properties
- 60851-4 Chemical properties
- 60851-5 Electrical properties
- 60851-6 Thermal properties

### Advantages

Excellent resistance to thermal overcharges and to mechanical strains. Good behavior when exposed to nuclear radiations and in cryogenic conditions.

### Order Data

The designation shall comprise:

Shape of the wire:	Flat
Designation of the insulation:	THERMEX 240
Coating class:	Grade 2
Nominal dimension in mm:	2.24 x 5.00
Reel type: e.g.:	DIN 500

Example of complete order:

2000 kg FL TX 240 G2 2.24 x 5.00 mm D500

### Characteristics of Thermex 240

	unit	value	Test standard
<b>Mechanical properties</b>			
Insulation increase Grade 1	mm	0.06 - 0.11	IEC60851-2
Insulation increase Grade 2	mm	0.12 - 0.17	IEC60851-2
Elongation at break thickness up to 2.5 mm	%	≥ 30	IEC60851-3 test 6
Elongation at break thickness above 2.5 mm	%	≥ 32	IEC60851-3 test 6
Springiness	°	≤ 5.0	IEC60851-3 test 7
Adherence after elongation	20 %	No loss of adhesion	IEC60851-3 test 8
Flexibility - edgewise bent on mandrel Ø 2 x width		no cracks	IEC60851-3 test 8
Flexibility - flatwise bent on mandrel Ø 2 x thickness		no cracks	IEC60851-3 test 8
<b>Electrical properties</b>			
Break down voltage Grade 1	V	≥ 1000	IEC60851-5 test 13
Break down voltage Grade 2	V	≥ 2000	IEC60851-5 test 13
<b>Thermal properties</b>			
Heat shock 30 min /260 °C mandrel Ø 2 x width		no cracks	IEC60851-6 test 9
Thermal endurance	TI	240	IEC60172

### Appearance

Slight color variations are raw material or process-related and have no influence on the technical properties of the wire.

The product properties set forth in this data sheet are based on the results of testing of typical material produced by the company Delle Fil SAS. Some variation in product properties is typical. Comments or suggestions relating to any subject other than product properties are offered only to call the end-user's or other person's attention to considerations which may be relevant in the independent determination of the use and/or manner of use of product. Delle Fil SAS does not claim or warrant that the use of its product will have the results described in this data sheet or that the information provided is complete, accurate or useful. The user should test the product to determine its properties and its suitability for the intended use. Delle Fil SAS expressly disclaims any liability for any damage, harm, injury, cost or expense to any person resulting directly or indirectly from that person's reliance on any information contained in this data sheet. Nothing contained in this data sheet constitutes representation or warranty as to any matter whatsoever. Delle Fil SAS makes no warranties whatsoever in this data sheet, expressed or implied, including any implied warranty or fitness for a particular use or purpose. Delle Fil SAS shall in no event be liable for incidental, exemplary, punitive or consequential damages.