

Taped wires

2FO 101 round

▪ Polyimide-Film taped copper wire

Description:

The winding wire 2FO 101 is a round copper wire wrapped tightly with 2 layers of Kapton®(Polyimide)-tape with 51 - 53 % overlap. Both tapes are coated on one side with a Teflon®-(FEP)-adhesive. A suitable heat treatment melts the thermoplastic FEP-coating and thus bonds firmly the overlapping films. This nonporous, highly flexible insulation of superior thermal, electrical and chemical resistance is typically utilized in oil pump motors.

Dimensions :

Round copper according to IEC 60317-0-1.

Insulation Construction:

Type	Construction:
2FO 101	Lapping with 2 layer, one side FEP-coated Polyimide film, thickness 0.04 mm, overlap 51 - 53 %

Standards:

Polyimide-film insulated round wires meet the requirements of IEC 60317-43 , Class 240.

Applications:

2FO 101 insulated wires are - due to their superior thermal, mechanical, dielectric and chemical properties - used especially where traditional wire insulations are inadequate.

Processing instructions:

Because of the excellent adherence of the insulation to the conductor, the low friction properties and mechanical toughness, such insulated wires can be processed on all common types of winding and coil forming machines.

- Nevertheless, when forming coils, the use of hard or sharp-edged tools is to be avoided.
- The best method for stripping the insulation of these wires is the mechanical one (using hand cutting tools or rotary knives).

			Value	Test norm
Increase in insulation				
Thickness increase due to insulation	mm		0.44 +/- 0.05	
Mechanical properties				
Elongation at break	<= 2.5 mm	%	min. 30	IEC 60851-3, Test 6
	> 2.5 mm	%	min. 33	
Springiness	<= 1.6 mm	°	max. 30	IEC 60851-3, Test 7
	>1.6 mm	°	max. 5	
Adherence after elongation		10 %	no loss of adhesion	IEC 60851-3, Test 8
Electrical properties				
Breakdown voltage		V	min. 6 000	IEC 60851-5, Test 13
Mandrel 3 x wire diameter		V	aver. 8 000	
Nominal resistance D.C. at 20 °C	Ohm.mm ² /m	max.	0.01724	IEC 60851-5, Test 5
Thermal properties				
Heat shock at 260°C / 30 min.				
<= 1.6 mm, mandrel φ 5 mm			no cracks	IEC 60851-6, Test 9
>1.6 mm, 15 % elongation			no cracks	

Appearance

Slight color variations are raw material or process-related and have no influence on the technical properties of the wire

Order data :

Quantity, Designation and Mode of Supply

The designation shall contain:	
Type of wire	round (DR)
Nominal dimension e.g.	2.5 mm
Conductor material	Cu
Designation of the insulation	2FO 101

The mode of supply shall indicate the type of reel required, e.g. cylindrical reel according to IEC 60264-2 (identical with DIN 46399) or other types.

Example of complete order:
500 kg DR 2FO 101 2.50 mm, reels DIN 355

The product properties set forth in this data sheet are based on the results of testing of typical material produced by the company Delle Fil SAS. Some variation in product properties is typical. Comments or suggestions relating to any subject other than product properties are offered only to call the end-user's or other person's attention to considerations which may be relevant in the independent determination of the use and/or manner of use of product. Delle Fil SAS does not claim or warrant that the use of its product will have the results described in this data sheet or that the information provided is complete, accurate or useful. The user should test the product to determine its properties and its suitability for the intended use. Delle Fil SAS expressly disclaims any liability for any damage, harm, injury, cost or expense to any person resulting directly or indirectly from that person's reliance on any information contained in this data sheet. Nothing contained in this data sheet constitutes representation or warranty as to any matter whatsoever. Delle Fil SAS makes no warranties whatsoever in this data sheet, expressed or implied, including any implied warranty or fitness for a particular use or purpose. Delle Fil SAS shall in no event be liable for incidental, exemplary, punitive or consequential damages.

